

Nr.: **BOSI190710yJ**


Commissioner Gujarat Borosil Limited
1101, Crescenzo, G Block
Bandra Kurla Complex
Mumbai 400051
India

Test Material 3.2mm matt/matt, smoother side
Anl. 26.7.2019

Test Method BRDF

Results Reflected luminance at bright sunshine*: $L_{V,10^\circ} = 19'000 \text{ cd/m}^2$
(near normal incidence of 100'000 lx)


Scattering plot for bright sunshine (100'000 lx) for an incident angle of 10°:



* 20'000 cd/m² allowed for airport installations: "Certification Specifications and Guidance Material for Aerodromes Design", CS-ADR-DSN, Issue 2, 29 January 2015

Annex of Test Report: BOSI190710yJ

Luminance at bright sunlight (100'000 lx) for different incidence angles:



Scattering plots for bright sunlight (100'000 lx) from different incidence angles:

